TECHNICAL INFORMATION — AFRICA

TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307		
construction	ISO 2424	3-ply yarn, hank dyed
yarn content	ISO 2424	100% Wools of New Zealand
backing	ISO 2424	Ceneva
suitability	EN 1307	23 / 32 Heavy Domestic/ General contract use
pile weight	ISO 2424	1,350 gr/m^2
total weight	ISO 8543	2,480 gr/m^2
pile height	ISO 1766	5.2 mm
total thickness	ISO 1765	8.4 mm
tuft density	ISO 1763	67,000 tufts/m^2
width	CEN/TS 14159	4m
thermal resistance	ISO 8302	0.14 m^2 K/W
flammability	ISO 13501-1	Cfl-S1
impact sound insulation	ISO 140-8/717-2	25 dB

COLOURS

Antelope	Gecko
Oryx	
Lemur	
Macaw	
Marlin	

RATINGS AND INFORMATION



CE
EN 14041
EN 1307

CARPETS TESTED FOR A BETTER LIVING ENVIRONMENT
GUT

CONTACT INFORMATION

julie@thetailoredworkplace.co.uk

07545634473

www.thetailoredworkplace.co.uk